

COATED FABRIC PROPERTIES	TEST METHOD	REQUIREMENTS
Color	Visual	Black
Width (trimmed)	ASTM D 751-89, sec. 8	60"
Total Weight	ASTM D 751-89, sec. 10.2	35.0 ± 3.0 oz/yd <sup>2</sup>
Gauge	ASTM D 751-89, sec. 9	Record Only
Tongue Tear – Warp	ASTM D 751-89, sec. 22	50.0 lbs/in min.
Tongue Tear – Fill	ASTM D 751-89, sec. 22	40.0 lbs/in min.
Grab Tensile – Warp	ASTM D 751-89, sec. 11	450.0 lbs/in min.
Grab Tensile – Fill	ASTM D 751-89, sec. 11	400.0 lbs/in min.
Adhesion – Face to Face	Fed. Std. 191A, Method 5970	10.0 lbs/in. min.
Adhesion – Back to Back	Fed. Std. 191A, Method 5970	10.0 lbs/in. min.
Flame Resistance (Flame) Warp Fill	Fed. Std. 191A, Method 5903	5.0 seconds max. 5.0 seconds max.
Flame Resistance (Char) Warp Fill	Fed. Std. 191A, Method 5903	3.0 inches max. 3.0 inches max.
Taber Abrasion – Side 1 (H-22 wheels, 1000 gm load, 1 <sup>st</sup> sign of show thru)	ASTM D 3389-94, Method A	2000 cycles min.
Taber Abrasion – Side 2 (H-22 wheels, 1000 gm load, 1 <sup>st</sup> sign of show thru)	ASTM D 3389-94, Method A	2000 cycles min.
State of Cure – Side 1	Trelleborg Test Method	Pass
State of Cure – Side 2	Trelleborg Test Method	Pass

Original Date: 07/10

Data presented are averaged results and should not be construed as specification limits.

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Reeves Brothers, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

